

IPOCLORIDO DI SODIO

(NaOCl)

CONCENTRAZIONE (in soluzione acquosa)	TEMPERATURA (C°)	PVC - U	PE	PP	PP - GF30	PVDF	PTFE	FEP, PFA	PA12	PSU	V2A 1, 4301	V4A, 4571	Hast - C 2, 4537	NBR	EPDM	FKM = FPM	CSM	FFKM	SSIC	Carbon	Al2O3	Al2O3 Sensor
5%	20	+	+	+	+	+	+	+			-	-	+	-	+	+	+	+	+	-	+	+
5%	40	+	0	0	0	0	+	+					+		0	+	+	+	+		+	+
5%	60	0	-	-	-	0	+	+										+	+			
5%	80					-	+	+										+	+			
5%	100						+	+										+	+			
12,5%	20	+	0	0	0	+	+	+	-		-	-	+	-	+	+	+	+	+	-	+	+
12,5%	40	+	0	-	-	0	+	+					+		-	+	+	+	+		+	+
12,5%	60	0				-	+	+										+	+			
12,5%	80						+	+										+	+			
12,5%	100						+	+										+	+			
15%	20	+	-	-	-	+	+	+	-		-	-	+	-	0	+	+	+	+	-	+	+
15%	40	+				0	+	+					+		-	+	+	+	+		+	+
15%	60					-	+	+										+	+			
15%	80						+	+										+	+			
15%	100						+	+										+	+			